

P/N NAS464-3-3

Description

Fastener Length: 9/16", Thread: 10-32, Thread Length: 23/64"

* Manufacturer certifications are shipped with your order FREE of charge

Order this part online

Additional Information

SKU / Model:	NAS46433
Minimum Qty (MOQ):	5 EA
NSN:	5306-00-286-1445
Schedule B:	7318.15.8085
ECCN:	EAR99
National Motor Freight:	093486, Bolts, nuts Or Screws, Noi (sub 3)



^{*} See page 2 for technical characteristics

P/N NAS464-3-3 Specifications

Thread Direction: Right-hand Thread Length: 0.321 Inches Minimum And 0.374 Inches Maximum Fastener Length: 0.515 Inches Minimum And 0.562 Inches Maximum Head Style: Hexagon Head Height: 0.94 Inches Nominal Wildth Between Flats: 0.365 Inches Minimum And 0.377 Inches Maximum Grip Diameter: 0.188 Inches Minimum And 0.1894 Inches Maximum Shank Unthreaded Hole Diameter: 0.070 Inches Nominal First Hole Single Shear Strength: 0.190 Inches Nominal First Hole Grip Length: 0.190 Inches Nominal First Hole Grip Length: 0.190 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 0.360 Inches Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches First Maximum First Hole And 0.392 Inches Maximum First Hole Center: 360 Inches First Maximum First Hole Center: 360 Inches First Maximum First Hole Cen	Thread Class:	3a
Thread Length: 0.327 Inches Minimum And 0.374 Inches Maximum Fastener Length: 0.515 Inches Minimum And 0.562 Inches Maximum Head Style: Hexagon Head Height: 0.94 Inches Nominal Width Between Flats: 0.365 Inches Minimum And 0.377 Inches Maximum Grip Diameter: 0.1889 Inches Minimum And 0.1894 Inches Maximum Shank Unthreaded Hole Diameter: 0.707 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Nominal Thread Diameter: 0.190 Inches Original Length: 0.190 Inches Nominal Grip Length: 0.190 Inches Nominal Minimum Tensile Strength: 0.190 Inches Nominal Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: 36.0 Rockwell C Minimum First Hole And 0.392 Inches Maximum First Hole Material Document And Classification: Steel Comp 4140 Overall Or Steel Comp £4340 Overall Or Steel Comp £730 Overall Or Mils-6098 Mil Spec 1th Material Response Overall Or Mils-8098 Mil Spec 2nd Material Response Overall Or Mils-8098 Mil Spec 2nd Material Response Overall Or Mils-8098 Mil Spec 4th Material Response Overall Or Mils-8098 Mil Spec 5th Mate		
Fastener Length: 0.515 Inches Minimum And 0.562 Inches Maximum Head Style: Hexagon Head Height: 0.94 Inches Nominal Width Between Flats: 0.365 Inches Minimum And 0.377 Inches Maximum Grip Diameter: 0.1889 Inches Minimum And 0.1894 Inches Maximum Shank Unthreaded Hole Diameter: 0.707 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Mominal Thread Diameter: 0.190 Inches Onisinal Thread Diameter: 0.188 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 35.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Hardness Rating: 35.0 Rockwell C Minimum First Hole And 0.392 Inches Maximum First Hole Bearing Surface To Shank Hole Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Material Document And Classification: Mils-5626 Mil Spec 1st Material Response Overall Or Mils-5098 Mil Spec 2nd Material Response Overall Or Mils-8693 Mil Spec 5th Material Response Overall Or Mils-8698 Mil Spec 3th Material Response Overall Or Mils-8698 Mil Spec 5th Material Response Overall Or Mils-8698 Mil Spec 5th Material Response Overall Or Mils-8698 Mil Spec 5		
Head Style: Hexagon Head Height: 0.094 Inches Nominal Width Between Flats: 0.365 Inches Minimum And 0.377 Inches Maximum Grip Diameter: 0.1889 Inches Minimum And 0.1894 Inches Maximum Shank Unthreaded Hole Diameter: 0.070 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Nominal Thread Diameter: 0.190 Inches Grip Length: 0.188 Inches Nominal Thread Quantity Per Inch: 3 1 Stream Fasting: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest 36.0 Rockwell C Minimum First Hole And 0.392 Inches Maximum First Hole Bearing Surface To Shank Hole Center: 36.0 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material: 36.0 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material Document And Classification: Milis-5626 Mil Spec 1st Material Response Overall Or Milis-5000 Mil Spec 2nd Material Response Overall Or Milis-6049 Mil Spec 3rd Material Response Overall Or Milis-6049 Mil Spec 6th Material Response Overall Or Milis-6049 Mil Spec 6th Material Response Overall Or Milis-6040 Milis-8695 Mil Spec 6th Material Response Overall Or Milis-6040 Milis-8695 Mil Spec 6th Material Res		
Head Height: 0.094 Inches Nominal Width Between Flats: 0.365 Inches Minimum And 0.1894 Inches Maximum Grip Diameter: 0.707 Inches Nominal First Hole Shank Unthreaded Hole Dlameter: 0.707 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Nominal Thread Diameter: 0.190 Inches Grip Length: 0.188 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest 36.0 Rockwell C Minimum First Hole And 0.392 Inches Maximum First Hole Bearing Surface To Shank Hole 0.360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Center: 3.80 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material: Steel Comp 4140 Overall Or Steel Comp £4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp £407 Overall Or Mil-s-5090 Mil Spec 2nd Material Response Overall Or Mil-s-6049 Mil Spec 3rd Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 4th Material Response Overall Or Mil-s-8695 Mil Spec 5th		
Width Between Flats: 0.365 Inches Minimum And 0.377 Inches Maximum Grip Diameter: 0.1889 Inches Minimum And 0.1894 Inches Maximum Shank Unthreaded Hole Diameter: 0.070 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Nominal Thread Diameter: 0.190 Inches Grip Length: 0.188 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: 36.0 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material: Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Material Document And Classification: Mills-5626 Mill Spec 1st Material Response Overall Or Mills-5009 Mill Spec 2nd Material Response Overall Or Mills-6098 Mill Spec 6th Material Response Overall Or Mills-8033 Mill Spec 5th Material Response Overall Or Mills-8033 Mill Spec 5th Material Response Overall Or Mills-8034 Mill Spec 5th Material Response Overall Or Mi		
Grip Diameter: 0.1889 Inches Minimum And 0.1894 Inches Maximum Shank Unthreaded Hole Diameter: 0.070 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Nominal Thread Diameter: 0.190 Inches Grip Length: 0.188 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: 3.360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material: 5teel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Material Document And Classification: Mili-s-5626 Mil Spec 1st Material Response Overall Or Mili-s-5000 Mil Spec 2nd Material Response Overall Or Mili-s-6049 Mil Spec 3rd Material Response Overall Or Mili-s-8098 Mil Spec 6th Material Response Overall Or Mili-s-8095 Mil Spec 5th Material Response Overall Or Mili-s-8095 M		
Shank Unthreaded Hole Diameter: 0.70 Inches Nominal First Hole Single Shear Strength: 2690 Pounds Per Square Inch Nominal Thread Diameter: 0.198 Inches Grip Length: 0.188 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: 360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material: Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Material Document And Classification: Mils-s-5626 Mil Spec 1st Material Response Overall Or Mils-s-6098 Mil Spec 4th Material Response Overall Or Mils-s-8503 Mil Spec 5th Material Response Overall Or Mils-s-6098 Mil Spec 4th Material Response Overall Or Mils-s-8503 Mil Spec 5th Material Response Overall Or Mils-s-6098 Mil Spec 4th Material Response Overall Or Mils-s-8503 Mil Spec 5th Material Response Overall Or Mils-s-6098 Mil Spec 4th Material Response Overall Or Mils-s-8503 Mil Spec 5th		
Single Shear Strength:2690 Pounds Per Square InchNominal Thread Diameter:0.190 InchesGrip Length:0.188 Inches NominalThread Quantity Per Inch:32Minimum Tensile Strength:160000 Pounds Per Square InchHardness Rating:36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum OverallDistance From Head Largest Bearing Surface To Shank Hole Center:3.360 Inches Minimum First Hole And 0.392 Inches Maximum First HoleMaterial:Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 40437 OverallMaterial Document And Classification:Miles-5626 Mil Spec 1st Material Response Overall Or Miles-5000 Mil Spec 2nd Material Response Overall Or Miles-6049 Mil Spec 3rd Material Response Overall Or Miles-6098 Mil Spec 4th Material Response Overall Or Miles-8503 Mil Spec 5th Material Response Overall Or Miles-8695 Mil Spec 6th Material Response OverallSurface Treatment:Cadmium ThreadsSurface Treatment Document And Classification:Q-p-416.type 2,class 3 Fed Spec Single Treatment Response HeadSurface Treatment Document And Classification:Q-p-416.type 2,class 3 Fed Spec Single Treatment Response Threads		
Nominal Thread Diameter: 0.190 Inches Grip Length: 0.188 Inches Nominal Thread Quantity Per Inch: 32 Minimum Tensile Strength: 160000 Pounds Per Square Inch Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: 36.0 Inches Minimum First Hole And 0.392 Inches Maximum First Hole Material: Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Material Document And Classification: Mil-s-5626 Mil Spec 1st Material Response Overall Or Mil-s-5000 Mil Spec 2nd Material Response Overall Or Mil-s-6049 Mil Spec 3rd Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Surface Treatment: Cadmium Threads Surface Treatment Document And Classification: Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Head Surface Treatment Document And Classification: Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads		
Grip Length: 10.188 Inches Nominal 11. Thread Quantity Per Inch: 12. I60000 Pounds Per Square Inch 13. I60000 Pounds Per Square Inch 14. If you want Inch 15. If you want Inch 16. If you want Inch 16. If you want Inch 17. If you want Inch 18. If you wa		
Thread Quantity Per Inch:32Minimum Tensile Strength:160000 Pounds Per Square InchHardness Rating:36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum OverallDistance From Head Largest Bearing Surface To Shank Hole Center:0.360 Inches Minimum First Hole And 0.392 Inches Maximum First HoleMaterial:Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 OverallMaterial Document And Classification:Mil-s-5626 Mil Spec 1st Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec St Materi	Nominal Thread Diameter:	0.190 Inches
Minimum Tensile Strength: Hardness Rating: 36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall Distance From Head Largest Bearing Surface To Shank Hole Center: Material: Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Mil-s-5626 Mil Spec 1st Material Response Overall Or Mil-s-5000 Mil Spec 2nd Material Response Overall Or Mil-s-6049 Mil Spec 3rd Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8505 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or	Grip Length:	0.188 Inches Nominal
Hardness Rating: Distance From Head Largest Bearing Surface To Shank Hole Center: Material: Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Mil-s-5626 Mil Spec 1st Material Response Overall Or Mil-s-5000 Mil Spec 2nd Material Response Overall Or Mil-s-6049 Mil Spec 3rd Material Document And Classification: Surface Treatment: Surface Treatment: Surface Treatment Document And Classification: Surface Treatment Document And Classification:	Thread Quantity Per Inch:	32
Distance From Head Largest Bearing Surface To Shank Hole Center: Material: Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 Overall Material Document And Classification: Surface Treatment: Cadmium Threads Surface Treatment Document And Classification: Surfa	Minimum Tensile Strength:	160000 Pounds Per Square Inch
Bearing Surface To Shank Hole Center:0.360 Inches Minimum First Hole And 0.392 Inches Maximum First HoleMaterial:Steel Comp 4140 Overall Or Steel Comp E4340 Overall Or Steel Comp 8740 Overall Or Steel Comp 8735 Overall Or Steel Comp 6150 Overall Or Steel Comp 4037 OverallMaterial Document And Classification:Mil-s-5626 Mil Spec 1st Material Response Overall Or Mil-s-6049 Mil Spec 3rd Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8503	Hardness Rating:	36.0 Rockwell C Minimum Overall And 40.0 Rockwell C Maximum Overall
Material Document And Classification: Material Document And Classification: Mil-s-5626 Mil Spec 1st Material Response Overall Or Mil-s-5000 Mil Spec 2nd Material Response Overall Or Mil-s-6049 Mil Spec 3rd Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8	Bearing Surface To Shank Hole	0.360 Inches Minimum First Hole And 0.392 Inches Maximum First Hole
Material Document And Classification: Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 6th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Spec 5th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or Mil-s-8695 Mil Sp	Material:	
Surface Treatment Document And Classification: Cadmium Head Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Head Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads		Material Response Overall Or Mil-s-6098 Mil Spec 4th Material Response Overall Or Mil-s-8503 Mil Spec 5th Material Response Overall Or
Surface Treatment Document And Classification: Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Head Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads	Surface Treatment:	Cadmium Threads
Classification: Surface Treatment Document And Classification: Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Head Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads	Surface Treatment:	Cadmium Head
Classification: Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads		Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Head
Thread Series Designator: Unf		Qq-p-416,type 2,class 3 Fed Spec Single Treatment Response Threads
	Thread Series Designator:	Unf

How to Order Order this bolt from our inventory online by visiting https://military-fasteners.com/bolts/machine+bolts/NAS464-3-3 and selecting the quantity you want then click "add to cart". Once items are in your cart you can check out here to complete your order.